

Excalibur® 7018 MR®

Mild Steel, Low Hydrogen • AWS E7018 H4R

Key Features

- ▶ Premium arc performance
- ▶ Square coating burn-off
- ▶ Easy strike and re-strike
- ▶ Effortless slag removal
- ▶ Minimal spatter for enhanced operability and clean weld surface

Typical Applications

- ▶ Mild steel
- ▶ Pressure vessels
- ▶ Power generation
- ▶ Pressure piping
- ▶ Petrochemical

Conformances

AWS A5.1/A5.1M: 2004	E7018 H4R
ASME SFA-A5.1:	E7018 H4R
ABS:	3Y H5
Lloyd's Register:	3YM H5
DNV Grade:	3 YH5
GL:	3YH5
BV Grade:	3YHHH
CWB/CSA W48-06:	E4918
EN ISO 2560-B:	E4918 A H5

Welding Positions

All, except vertical down

DIAMETERS / PACKAGING

Diameter in (mm)	Length in (mm)	1 lb (0.5 kg) Plastic Tube 6 lb (2.7 kg) Master Carton	10 lb (4.5 kg) Easy Open Can 30 lb (13.6 kg) Master Carton	50 lb (22.7kg) Carton
3/32 (2.4)	14 (350)	ED032086	ED032588	ED028280
1/8 (3.2)	14 (350)	ED031468	ED032589	ED028281
5/32 (4.0)	14 (350)		ED032590	ED028282
3/16 (4.8)	14 (350)			ED028283
7/32 (5.6)	18 (450)			ED028917
1/4 (6.4)	18 (450)			ED028918

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.1/A5.1M: 2004

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft•lbf) @ -29°C (-20°F)
Requirements - AWS E7018 H4R	400 (58) min.	490 (70) min.	22 min.	27 (20) min.
Typical Results ⁽³⁾ - As-Welded	430-510 (62-74)	510-605 (74-88)	25-37	121-332 (89-246)

DEPOSIT COMPOSITION⁽¹⁾ – As Required per AWS A5.1/A5.1M: 2004

	%C	%Mn	%Si	%P	%S	%Ni
Requirements - AWS E7018 H4R	0.15 max.	1.60 max.	0.75 max.	0.035 max.	0.035 max.	0.30 max.
Typical Results ⁽³⁾	0.03-0.08	1.01-1.55	0.34-0.68	0.01-0.02	≤ 0.01	0.01-0.06
	%Cr	%Mo	%V	%Mn + Ni + Cr + Mo + V	Diffusible Hydrogen (mL/100g weld metal)	
Requirements - AWS E7018 H4R	0.20 max.	0.30 max.	0.08 max.	1.75 max.	4.0 max.	
Typical Results ⁽³⁾	0.02-0.07	≤ 0.05	≤ 0.02	1.04-1.75	2-3	

TYPICAL OPERATING PROCEDURES

Polarity ⁽⁴⁾	Current (Amps)					
	3/32 in (2.4 mm)	1/8 in (3.2 mm)	5/32 in (4.0 mm)	3/16 in (4.8 mm)	7/32 in (5.6 mm)	1/4 in (6.4 mm)
DC+	70-110	90-160	130-210	180-300	250-330	300-400
AC	80-120	100-160	140-210	200-300	270-370	325-420

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer below. ⁽⁴⁾Preferred polarity is listed first.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.